

Romana:

In cadrul primei activitatii au fost obtinete noi formulari multifunctionale pe baza de chitosan (Ch) si biosticla (BG) prin Evaporarea Laser Pulsată Asistată Matricial (MAPLE). In acest studiu depunerea a fost realizata pe un suport de 73Ti-20Zr-5Ta-2Ag. Parametrul important care caracterizeaza o suspensie este potentialul Zeta (ζ). Potențialul ζ determină stabilitatea particulei în suspensie, direcția de mișcare (depunere catodică sau anodică), mobilitatea particulei și densitatea filmului.

Pentru realizarea suspeniei, folosita la depunere, au fost realizate mai multe esantioane ce contin Ch, BG si ZnO in diverse rapoarte de masa ce ulterior au fost caracterizate.

In cadrul celei de a doua activitatii este prezentata tehnica de depunere MAPLE ca metoda pentru producerea filmelor uniforme, compuse din specii cu greutăți moleculare diferite, cu morfologii unice folosind avantajele depunerii din vid. Procesul de depunere a filmelor poliomerice prin MAPLE implică absorbția luminii cu o anumită lungime de undă produsa de un laser de către un amestec diluat și inghetat de polimer (substanta de interes) cu o concentrație mai mică de 5% și solvent relativ volatil (matrice), astfel incat substanta de interes sa fie protejata de o cantitate mare de solvent. În timpul procesului de depunere, în mod ideal, cea mai mare parte a energiei laser ar trebui absorbită de moleculele de solvent, reducând astfel la minimum sau evitând în totalitate degradarea fotochimică a polimerului.

S-au efectuat incercari de depunere prin acesta metoda pe aliajul de 73Ti-20Zr-5Ta-2Ag utilizand discuri de 2 cm diametru, și 1 mm grosime. Depunerea a fost optimizată în funcție de fluента laserului și de presiunea în interiorul camerei de lucru. Cea mai bună combinație a fost găsită pentru $0,5 \text{ J/cm}^2$ și 1 Pa. A fost aplicată o serie de 25 000 de impulsuri laser folosind un laser KrF, cu $\lambda=248\text{nm}$.

In cadrul celei de a treia activitatii s-a efectuat caracterizarea substraturilor obtinute prin analize de suprafața cuplate cu tehnici compozitionale: SEM și EDX, FT-IR, unghi de contact, masuratori de rugozitate, datele obtinute fiind în buna concordanță cu obiectivele propuse.

English:

In the first activity, new multifunctional formulations based on chitosan (Ch) and bioglass (BG) were obtained through Matrix Assisted Pulsed Laser Evaporation (MAPLE). In this study, the deposition was carried out on a 73Ti-20Zr-5Ta-2Ag support. The important parameter that characterizes a suspension is the Zeta potential (ζ). The ζ potential determines the stability of the particle in suspension, the direction of movement (cathodic or anodic deposition), the mobility of the particle and the density of the film. To make the suspension used for deposition, several samples were made containing Ch, BG and ZnO in various mass ratios that were later characterized.

In the second activity, the MAPLE deposition technique is presented as a method for producing uniform films, composed of species with different molecular weights, with unique morphologies using the advantages of vacuum deposition. The process of deposition of polymeric films by MAPLE involves the absorption of light with a certain wavelength produced by a laser by a diluted and frozen mixture of polymer (substance of interest) with a concentration of less than 5% and relatively volatile solvent (matrix), so that the substance of interest is protected by a large amount of solvent. During the deposition process, ideally, most of the laser energy should be absorbed by the solvent molecules, thus minimizing or completely avoiding the photochemical degradation of the polymer. Deposition tests were carried out using this method on the 73Ti-20Zr-5Ta-2Ag alloy using discs of 2 cm diameter and 1 mm thickness. The deposition was optimized depending on the laser fluence and the pressure inside the working chamber. The best combination was found for 0.5 J/cm² and 1 Pa. A train of 25,000 laser pulses was applied using a KrF laser with =248nm.

In the third activity, the characterization of the substrates obtained through surface analysis coupled with compositional techniques was carried out: SEM and EDX, FT-IR, contact angle, roughness measurements, the data obtained being in good agreement with the proposed objectives.